

IN STOCK - immediately available

TPU-compound - injection molded quality in natural and black

Polylan 20s series

- Plain polyester (may contain parts of polyether)
- Minimal variations in color and processability from batch to batch are possible
- Suitable for applications with simple to medium technical requirements
- Polyester based injection molding from Shore A70 to Shore D60

Art.-No.	Description	Colour	Shore Hardness A DIN ISO 7619-1	Tensile strength N/mm ² DIN 53504-S2	Elongation at break in % DIN 53504-S2	Density g/cm ³ DIN EN ISO 1183-1
UC2-27520	Polylan 27520	natural	75 +/- 3	>23	> 350	1,21+/-0,04
UC2-28020	Polylan 28020	natural	80 +/- 3	>23	> 350	1,21+/-0,04
UC2-28520	Polylan 28520	natural	85 +/- 3	> 26	> 350	1,21+/-0,04
UC2-29020	Polylan 29020	natural	90 +/- 3	> 26	> 350	1,21+/-0,04
UC2-29520	Polylan 29520	natural	95 +/- 3	> 26	> 350	1,21+/-0,04
UC2-27020S	Polylan 27020S	black	70 +/- 3	>23	> 350	1,21+/-0,04
UC2-27520S	Polylan 27520S	black	75 +/- 3	>23	> 350	1,21+/-0,04
UC2-28020S	Polylan 28020S	black	80 +/- 3	>23	> 350	1,21+/-0,04
UC2-28520S	Polylan 28520S	black	85 +/- 3	> 26	> 350	1,21+/-0,04
UC2-29020S	Polylan 29020S	black	90 +/- 3	> 26	> 350	1,21+/-0,04
UC2-29520S	Polylan 29520S	black	95 +/- 3	> 26	> 350	1,21+/-0,04

Our stock items are packed in 25 kg bags as standard. On request, the goods can also be packed in an octabin for purchases of at least 500 kg.

Application spectrum



More information can be found on our website at: www.polytherm-kg.de
or contact us directly at: sales@polytherm-kg.de

The values listed above are average values that were determined statistically on the basis of samples, without being guaranteed as a property. They do not release the buyer from an incoming goods inspection.